

**ESLON-DC Polycarbonate PC 407 AS / PC 427 AS
Chemical Resistance**

CHEMICALS	Methods	A	B
	Content (%)		
Hydrofluoric acid	20	+	+
Hydrochloric acid	20	+	+
Sulfuric acid	50	+	+
Nitric acid	20	+	+
Phosphoric acid	85	+	+
Acetic acid	10	+	+
Caustic soda	30	-	+
Caustic potash	30	-	+
Hydrogenperoxide	30	+	+
Ammoniumfluoride	sat.	-	+
Potassium chloride	sat.	+	+
Sodium chloride	sat.	+	+
Ammonia	100	+	-
Alcohols (Methyl, Ethyl)	100	+	+
Isopropyl alcohol (+)	100	+	+
Ketones (acetone, MEK)	100	-	-
Aromatics (benzene, toluene)	100	-	-
Esters (ethyl acetate, butyl acetate)	100	-	-
Halogens (Methylene chloride)	100	-	-
Formalin	100	+	+
Freon (TES)	30	+	+
Water	100	+	+
Washing-up liquid (*)	-	+	+
Glass cleaner (*)	-	+	+

Description of the methods:

Method A: Immersion condition: 72 hours (23°C room temperature)

Method B: Applying of 5ml liquid and 12 hours of immersion

Result:

+ : not affected

- : surface whitening and/or swelling of the base material

Remarks:

(+) especially recommended cleaning solution

(*) composition of washing-up liquid:

15-30% anionic tensides, nonionic tensides: 5-15%, less than 5% amphoteric tensides

(*) composition of glass-cleaner:

less than 5% anionic tensides, nonionic tensides, amphoteric tensides