

ESLON-DC TECHNICAL CHARACTERISTICS



STATIC DISSIPATIVE (CONDUCTIVE) PLASTIC SHEETS

TYPE	Polycarbonate
CODE	PC 407 AS
COLOUR	clear
VERSION	ESD-Standard

ELECTRICAL	METHOD	
Surface Resistivity	ASTM D-257	DIN 53482
Electrostatic Discharge	MIL B-81705B	
Dielectric Constant	ASTM D-150	DIN 53483

UNIT	
Ω / \square	$10^6 \sim 10^7$
sec	< 0.1
-	3

PHYSICAL		
Specific Gravity	ASTM D-792	DIN 53479
Water Absorption	ASTM D-570	DIN 53495
Pencil Hardness Surface	JIS K 5400	
Adhesion Strength Surface	JIS D 0202	

g/cm ³	1.20
%	0.3
Skala	HB
-	100/100

OPTICAL		
Transmittance (Clarity)	ASTM D-1003	
Refractive Index	ASTM D-1003	
Haze	ASTM D-542	
Distinctness of Image	JIS K 7105	

%	80
%	4
-	1.58
%	60

MECHANICAL		
Tensile Strength	ASTM D-638	DIN 53455
Tensile Elongation, Break	ASTM D-638	DIN 53455
Flexural Strength, Yield	ASTM D-790	DIN 53452
Flexural Modulus	ASTM D-790	
Compressive Strength	ASTM D-695	
Charpy Impact Strength (23°C)	JIS K 7110	
Notched IZOD Impact Strength	ASTM D-256	

N/mm ²	64.7
%	100
N/mm ²	93.2
N/mm ²	2600
N/mm ²	85.3
kJ/m ²	83.4
J/m	847

THERMAL		
Deflection Temperature	ASTM D-648	
Linear Expansion Coefficient	ASTM D-696	
Heat Conductivity	ASTM C-177	
Specific Heat	ASTM C-177	
Heat Shrinkage	JIS K 6745	
Flammability	UL-94	

°C	135
l/°C	7×10^{-5}
W/mK	0.20
kJ/kgK	1.26
%	
-	

ADvanced Plastics GmbH & Co. KG
 Poststrasse 21
 D- 33181 Fürstenberg
 Tel. (+ 49) 29 53 - 96 66 21 Fax. (+ 49) 29 53 - 96 66 22
 e-mail : info@advancedplastics.de Web.: www.advancedplastics.de

If not otherwise mentioned all data refer to a sheet thickness of 3mm.
 All data show the typical values, no guaranteed values for specification purpose.
 Date of publication: 31.01.2007